

ABSTRACT OF THE DISCLOSURE

Methods are provided for inactivation of pathogens in biomaterials. Pathogen inactivating agents are added to and mixed with biomaterials in an additive solution that is low in chloride and/or hypotonic, resulting in substantial increases in inactivation of bacterial pathogens, particularly Gram negative bacterial pathogens.